

Test Report

No. AJFS1711010684FF

Date: DEC.08, 2017

Page 1 of 3

ALUVERO PTY LTD

2/23 ORCHARD CRESCENT, MONT ALBERT NORTH, VICTORIA, AUSTRALIA

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: ALUVERO CELLULOSE FIBER CEMENT BOARDS AUTOCLAVED

SGS Ref No.: NJIN1711004639ML Manufacturer: ALUVERO PTY LTD

Test Requested:

AS/NZS 1530.3:1999 Methods for fire tests on building materials, components and structures. Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release.

Test Results: -- See attached sheet --

Test Period:

Sample Receiving Date : NOV.28, 2017

: NOV.28, 2017 TO DEC.06, 2017

Test Performing Date Signed for

and on behalf of <u>SGS-CSTC Co.</u>, Ltd. Anji Branch

Allen Zou

Technical Manager





Test Report

No. AJFS1711010684FF

Date: DEC.08, 2017

Page 2 of 3

I. Test conducted

This test was performed in accordance with" AS/NZS 1530.3:1999 Methods for fire tests on building materials, components and structures. Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release."

II. Sample details

Description / Color	Aluvero Cellulose Fiber Cement Boards Autoclaved / Wheat	
Thickness	About 17.5mm	
Density	About 144 kg/m ³	
Sample Dimension	450mm×600mm	

	Temperature (°ℂ)	Humidity (%)	Duration (d)
Conditioning	20±2 °ℂ	65±5%	5

Note: The specimens shall be conditioned to constant mass.

Mounting or fixing method for test sample:

Using fibre-reinforced cement board as substrate, held the sample and substrate against the specimen support frame by use the specimen clamping ring. No joint in the specimen.

III. Test results

The mean values and standard errors:

Items		Mean value	Standard error
Ignition Time, (min)		NI	NI
Flame propagation time, (s)		NA	NA
Heat release integral, (Kj/m²)		NA	NA
Maximum optical density, D (m ⁻¹)	Ignition specimen	1	1
	Non-ignition specimen	0	0
	Ignition specimen	1	1
Smoke release , lg D	Non-ignition specimen	NA	NA

Note: 1) Where all specimens do not ignite, means and standard errors for smoke release shall be reported separately for those specimens that ignite and those that do not ignite. The higher of the two values shall be reported as the smoke released for the material or component.

2) Where all specimens do not ignite, indices for smoke developed shall be reported separately for those specimens that ignite and those specimens that do not ignite. The higher of the two values shall be reported as the smoke developed index for the product.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printe overleaf, available on request or accessible at http://www.sgs.com/en/Tems-and-Conditions.apx.and, for electronic Documents at http://www.sgs.com/en/Terms-e-Document.aspx tattention is drawn to the limitation of ilability, indemnification and jurisdiction issues defined therein. Any holder of this document is divised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of clients instructions, if any. The Company's sole responsibility is to its Client and this document does not excended parties to except in full, without prior written approval of the Company. Any unauthorized alteration, foreiry or falsification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the w. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention.To check the authenticity of testing / inspection report & certificate, please contact as telephone (86-755) 830*



Test Report No. AJFS1711010684FF Date: DEC.08, 2017 Page 3 of 3

Regulatory Indices:

Items	Regulatory Indices
Ignitability index (Range 0 to 20)	0
Spread of flame index (Range 0 to10)	0
Heat evolved index (Range 0 to 10)	0
Smoke developed index (Range 0 to 10)	0

Statement:

- 1) The results only apply to the specimen mounted as described in this report.
- 2) The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions.

Photo Appendix:



SGS authenticate the photo on original report only

End of Report

